


Prevention of Corrosion of Silver Reflectors for the National Ignition Facility

Norman Thomas, Wigbert Siekhaus
Joseph Farmer, Hugh Gregg
Al Erlandson, Chris Marshall
Jesse Wolfe, David Fix
David Ahre

This paper was prepared for submittal to the
International Symposium on Optical Science,
Engineering and Instrumentation
San Diego, CA
July 19-24, 1998

July 1999



DISCLAIMER

This document was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor the University of California nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or the University of California, and shall not be used for advertising or product endorsement purposes.

Prevention of Corrosion of Silver Reflectors for the National Ignition Facility

Norman Thomas, Wigbert Siekhaus, Joseph Farmer, Hugh Gregg,
Al Erlandson, Chris Marshall, Jesse Wolfe, David Fix and David Ahre
Lawrence Livermore National Laboratory
7000 East Avenue
Livermore, CA 94550

ABSTRACT

A durable protected silver coating^{1,2} was designed and fabricated for possible use on flashlamp reflectors in the National Ignition Facility (NIF) to avoid tarnishing under corrosive conditions and intense visible light (10 J/cm^2 , $360 \mu\text{s}$). This coating provides a valuable alternative for mirror coatings where high reflectance and durability are important requirements. This paper describes a protected silver coating having high reflectance from 400 nm to 10,000 nm. The specular reflectance is between 95% and 98% in the visible region and 98% or better in the infrared region.

1. INTRODUCTION

Evaporated silver on mirror substrates has several advantages compared to other metals. It has the highest reflectivity from 400 nm through the infrared and the lowest polarization splitting compared to any other metal. Figure 1 compares the reflectance for silver, aluminum and gold. The disadvantage of bare silver is that it tarnishes under ordinary atmospheric conditions and does not have a high reflectance below 400 nm. There is a minimum reflectance at 320 nm due to a surface plasmon resonance. Aluminum, on the other hand, has a dip in reflectance at 850 nm due to interband transitions³, but reflects well down to 280 nm, the cutoff for atmospheric transmission.




Fig. 1 Reflectance of evaporated metals in the visible and infrared.

Silver is a noble metal which is completely stable in aqueous solutions of any pH as long as oxidizing agents or complexing substances are not present. In the presence of such substances, the high specular reflectivity of silver is degraded by sulfidation, chloridation and oxidation with corrosive chemicals⁴⁻¹⁴ in the atmosphere such as H_2S , O , O^+ , H_2O_2 , SO_2 , Cl^- , etc. The corrosion products of silver are Ag_2S , AgCl , Ag_2O , Ag_2SO_4 and Ag_2CO_3 in increasing order of solubility. Since these products form in the thin water layer which is typically present on silver, the most likely precipitate is Ag_2S . Depending on its thickness, an absorbing Ag_2S film can reduce the Ag reflectance to zero. Similarly, the other corrosion

films can reduce the reflectance of Ag. For example, AgCl can photolytically decompose in the presence of light leaving metallic Ag which is the basis for some photographic films. The reflectance of an Ag₂S film grown on Ag versus film thickness is shown in Fig. 2 for three different wavelengths: 450, 500 and 650 nm.




Fig. 2 Reflectance of Ag₂S film on Ag versus film thickness

An Ag corrosion experiment showed that the growing film reduces the reflectance more strongly at the shorter wavelengths in complete agreement with the theoretical prediction above (Fig. 2). At physical film thicknesses approaching 20 nm, the reflectance of silver can be reduced to zero. Severely tarnished silver will appear black under these conditions.

2. THIN FILM DESIGN

The thin film design which may be a candidate for the NIF project is a durable enhanced silver high reflector based on a design presented by J. Wolfe^{15,16} at the OSA meeting in Tucson, Arizona, June 5-9, 1995. The design was modified to meet the optical and durability requirements for the NIF project. The coating must meet the following optical specifications:

$$\begin{aligned} R &> 95\% & 0^\circ \leq \theta \leq 60^\circ \\ R &> 90\% & 60^\circ < \theta \leq 80^\circ \end{aligned}$$

for the wavelength range 400 – 1000 nm. The basic coating design is shown in Fig. 3.




Fig. 3 Coating design

The adhesion layer provides nucleation sites on the substrate for the sputtered silver, and works in combination with the passivation layer to improve mechanical and chemical durability. The passivation layer alloys with the silver and helps in preventing sulfides, chlorides and oxides from reacting with the silver. The silicon nitride layer improves mechanical durability and acts as a barrier layer preventing corrodants from reacting with the silver. The metal oxide layers are combinations of silica, titania or niobia and serve to increase the reflectance.

The theoretical optical performance for this design at angles of incidence 20°, 40°, 60° and 80° and 400 – 1000 nm is shown in Fig. 4. This design meets the reflectance specification at non-normal incidence specified for the NIF project.




Fig. 4 Theoretical reflectance of coating design at angles of incidence 20°, 40°, 60°, and 80°.

3. PRELIMINARY COATING RUNS

Viratec Thin Films, Inc., in Faribault, Minnesota, provided their R&D facility and expertise for the coating. The design was coated on aluminum and stainless steel substrates using an Airco ILS-1600 sputter coater with a load-lock and DC magnetrons. Single layers of the various coating materials were coated onto separate aluminum substrates and characterized with a Woollam ellipsometer, Alpha Step profilometer, and Perkin Elmer Lambda 9 spectrophotometer. The adjusted design was coated onto diamond-paste polished aluminum substrates, stainless steel substrates, highly polished aluminum foil, and microscope slides overcoated with sputtered aluminum as a base layer. The coated microscope slides were scanned with a Perkin Elmer Lambda 9 spectrophotometer with an absolute reflectance attachment. The resulting scan at near-normal incidence is compared to theory in Fig. 4. The measured specular reflectance agrees to within 1% of the theoretical prediction. Several highly polished aluminum foils 0.030 inch thick and highly polished stainless steel 0.029 inch thick substrates were coated with the design which showed excellent results.




Fig. 5 Comparison of the measured coating reflectance to theory

4. ENVIRONMENTAL TEST RESULTS

The coated parts were tested according to Mil Spec 13508C. They successfully passed tape, cheese cloth, and humidity. An additional test was performed in the flashlamp test facility where a coated aluminum sample was subjected to flashes from an intense flashlamp in a normal Livermore atmosphere with naturally-occurring corrodants. After two months testing and 20,717 flashes, there was no detectable change in reflectance of the protected silver. During the same test, bare silver mirrors corroded and either peeled off the substrates or developed a haze on the silver which was probably due to the growth of Ag_2S micro-crystals. Some other over-coated silver mirrors also failed the test.

The reflectance of the successful protected silver mirror before and after exposure is shown in Fig. 6. The reflectance curves before and after exposure lie on top of one another to within 1%, the accuracy of the measurement. A diamond scribe was used to scratch through the top coating layers which were exposed to normal atmosphere without any apparent corrosion.

The reflectance of the same protected silver mirror was measured in the infrared. Fig. 7 shows the reflectance at normal incidence from 3 μm to 13 μm (3000 nm to 13,000 nm). The reflectance is typically very high in the infrared.




Fig. 6 Reflectance of protected silver mirror before and after 20,717 flashes and 2 months in a corrosive atmosphere.




Fig. 7 Measured reflectance of protected silver mirror in the infrared.

5. FUTURE DEVELOPMENT

The future development of protected silver coatings for mirrors may include extending the reflectance down to 300 nm. An initial coating design shows promise in achieving this goal. We are working towards the goal of preventing tarnishing for at least 30 years under normal atmospheric conditions. We are also seeking a method to strip these durable protected silver coatings from the substrate. One possibility is an underlayer which can be attacked by chemicals and remove the coating without deterioration to the substrate.

6. CONCLUSIONS

A durable protected silver coating was designed and coated on polished aluminum and stainless steel substrates, aluminum foils and microscope slides. This coating meets the optical performance specifications required for NIF. Initial testing according to mil-spec 13508C indicates that it has the mechanical and chemical durability required for the NIF flashlamp reflectors. Further accelerated testing under flashlamp irradiation while in a corrosive environment will be conducted in order to ascertain the corrosion rates to be expected over the 30-year lifetime of the National Ignition Facility. The results indicate that this durable protected silver coating may also be a good candidate for mirrors in telescopes, solar collectors located in the desert, and for military instruments.

7. ACKNOWLEDGMENT

This work was performed under the auspices of the U.S. Department of Energy by Lawrence Livermore National Laboratory under contract No. W-7405-Eng-48. The coating production runs described in this paper were carried out by Viratec Thin Films, Inc. under contract with Lawrence Livermore National Laboratory. The authors would like to acknowledge the contributions of Erik Bjornard, Dan Woodruff, Dan Bouillez, and Darin Glenn at Viratec Thin Films; and Wigbert Siekhaus, Dave Fix, Dave Ahre and Nan Poggio of LLNL.

8. REFERENCES

1. N. Thomas, J. Wolfe, J. Farmer, "Protected Silver Coating for Astronomical Mirrors," SPIE Astronomical Telescopes and Instrumentation Symposium, vol. 3352, 1998.
2. N. Thomas, J. Wolfe, J. Farmer, A. Erlandson, C. Marshall, D. Woodruff, D. Bouillez, D. Glenn, E. Bjornard, "Protected Silver Coating for National Ignition Facility Flashlamp Reflectors," OSA Optical Interference Coatings Topical Meeting, Tucson, Arizona, June 7-12, 1998
3. M.R. Jacobson, R. Kneale, K. Raybould, F.C. Gillett, R. Laird, R.P. Shimshock and D.C. Booth, "Development of silver coating options for the Gemini 8-m telescopes project", SPIE Astronomical Telescopes and Instrumentation Symposium, vol. 3352, 1998.
4. H.E. Bennett, R.L. Peck, D.K. Burge, J.M. Bennett, "Formation and growth of tarnish on evaporated silver films," J. Appl. Phys. 40 8, 3351-60 (1969).
5. D.W. Rice, P. Peterson, E.B. Rigby, P.B. Phipps, R.J. Cappell, R. Tremoureux, "Atmospheric corrosion of copper and silver," J. Electrochem. Soc. 128 2, 275-84 (1981).
6. B.T. Reagor, J.D. Sinclair, "Tarnishing of silver by sulfur vapor: film characteristics and humidity effects," J. Electrochem. Soc. 128 3, 701-5 (1981).
7. J.P. Franey, G.W. Kammlott, T.E. Graedel, "The corrosion of silver by atmospheric sulfurous gases," Corros. Sci. 25 2, 133-43 (1985).
8. T.E. Graedel, "Corrosion mechanisms for silver exposed to the atmosphere," J. Electrochem. Soc. 139 7, 1963-70 (1992).
9. W.M. Moore, P.J. Codella, "Oxidation of silver films by atomic oxygen," J. Phys. Chem. 92 15, 4421-6 (1988).
10. J. Fang, Y. Yu, "XPS and AES study on the tarnishing mechanism of silver-electroplated deposits. (II) Mechanism of tarnishing caused by exposure to light and sodium sulfide treatment," Huagong Xuebao 2, 171-8 (1985).
11. R.S. Saifullin, L.V. Zaitseva, I.N. Andreev, "Protection of silver surfaces from tarnishing," Zashch. Met. 2 5, 571-5 (1966).

12. V.V. Orekhova, F.K. Andryushchenko, A.G. Mozgovya, "Protection of silver from darkening by a chemical passivation method," *Zashch. Met.* 14 5, 629-32 (1978).
13. V. Daniels, "Plasma reduction of silver tarnish on Daguerreotypes," *Stud. Conserv.* 26 2, 45-9 (1981).
14. D.W. Rice, R.J. Cappell, W. Kinsolving, J.J. Laskowski, "Indoor corrosion of metals," *J. Electrochem. Soc.* 127 4, 891-901 (1980).
15. J. Wolfe, "Control of stress-corrosion cracking in thin film designs," 36th Annual Technical Conference Proceedings of the Society of Vacuum Coaters, Dallas, TX, April 25-30 (1993).
16. J.D. Wolfe, R.E. Laird, C.K. Carniglia, J.P. Lehan, "Durable silver-based antireflection coatings and enhanced mirrors," Topical Meeting on Interference Coatings, OSA, Tucson, AZ, June 5-9 (1995).